









Product Availability

Our continuously tapered fiber range is tabulated below.



Cross Sections		Base Polymers	Std. Lengths (mm)	Std. Tapers Mils (mm) Butt/Tip	Special Tapers Polyester (mm) Butt/Tip
	Solid Round	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.265/0.145; 64~76 - 0.275/0.155; 83~89 - 0.275/0.165; 95+ - 0.285/0.165.
	Ribbed	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.275/0.155; 64~76 - 0.29/0.165; 83~95 - 0.31/0.175; 102~114 - 0.33/0.185; 121+ - 0.35/0.195.
	Hollow Round	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.315/0.17; 64~76 - 0.315/0.18; 83~95 - 0.335/0.19; 102~114 - 0.355/0.20; 121+ - 0.37/0.21.
	Honeycomb (2HC)	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.315/0.17; 64~76 - 0.315/0.18; 83~95 - 0.335/0.19; 102~114 - 0.355/0.20; 121+ - 0.37/0.21.
	Honeycomb (3HC)	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.315/0.17; 64~76 - 0.315/0.18; 83~95 - 0.335/0.19; 102~114 - 0.355/0.20; 121+ - .37/0.21.
	Spoked	Polyester or Nylon (PA 6.12, 6.10 or 12)	51 to 140 (2" to 5.50")	09/05 (0.229/0.127); 12/08 (0.305/0.203); 15/10 (0.38/0.254)	51~57 - 0.315/0.165; 64~76 - 0.325/0.175; 83~95 - 0.335/0.185; 102~114 - 0.355/0.195; 121+ - 0.37/0.205.

DIAMETER TOLERANCES (MM)

Solid Round 5 mils $-0.017/+0.13$; 8 mils $0.018/+0.012$; 9 mils $-0.014/+0.016$; 12 mils ± 0.015 . Hollow shapes are difficult to measure as the extruded shape is not circular. We use an inline measurement system that confirms to ± 0.015 mm on the tip side and 0.02mm on the butt side.

LENGTH TOLERANCES (MM)

± 1 mm.

COLOURS

Standard colors are bristle white, black and gold. Custom colors are subject to MOQ and have a longer lead time.

SPECIALS

M-Cell functionality is available on all cross sections.

Bio-Based fibers are prepared mixtures using multiple cross sections and are supplied under our Vibris program.

DISCLAIMER

Our liability is limited to the value of the material supplied.

Nexstar Extrusions Pvt. Ltd.

31 A, Baikampady Industrial Area, Mangalore 575011, Karnataka, INDIA.

Tel +91 80 50 55 0505. Email: info@nexstargroup.com

www.nexstargroup.com